IN THE SPECIFICATION:

Please replace the paragraph beginning at line 19 of page 5 with the following amended paragraph.

An embodiment of the present invention provides the above-mentioned film obtained after the peeling which is a the multi-layer film wherein in which the layers (A) and (B) can be peeled from each other at a peel strength of 500 g/15 mm or less (measured at 23°C and a speed of 300 mm/minute in a T-shaped peel state on the basis of JIS K6854).